

LDX 2101®

High Strength Duplex Welded Stainless Tubular Products

Characteristics

LDX 2101® is a lean Duplex stainless steel with low Ni-content. Its high mechanical strength is similar to other Duplex grades and its good corrosion resistance is better than the 4307 (304L) grade (PRE). Combined, these properties can be utilized to get an optimized design with respect to strength, maintenance, durability and long-term cost efficiency.

Characteristic properties:

- High mechanical strength
- Good weldability
- Good corrosion resistance
- High Stress Corrosion Cracking (SCC) resistance
- Very good machinability
- Very good wear and abrasive resistance
- Low thermal expansion
- Good fatigue properties
- Temperature range -40°C to 250°C

Dimensions

Tubular products in grade LDX 2101® are not stock standard, but can be generally manufactured in most common standard sizes within OSTP's product range and to client tailored needs by agreement.

Tubes, Pipes and Butt Weld Fittings

- OD: 21.3–1219.0 mm
- WT: 1.5–25.4 mm
- Lengths: up to 12 m

Tubes below 21.3 mm OD and tubes with wall thickness below 1.5 mm or length over 12 m on special request. For additional information on tubular product availability in this grade also see OSTP's Duralite™ LDX 2101® Piping System information.

Executions

Tubes, Pipes and Butt Weld Fittings

- Welded with- or without filler metal
- Unannealed, pickled



- Solution annealed and pickled
- With – or Without BCW (Bead Cold Work) – Tubes Only
- Bevelled ends according to standards

Corrosion resistance

The corrosion resistance of LDX 2101® is good, and the grade is suitable for use in a wide range of applications and environments. LDX 2101® has a better corrosion resistance than 4307 (304L) (PRE) possibly a substitute (316L) in some cases. Like other Duplex stainless steels, LDX 2101® shows much better resistance to SCC than standard austenitic grades. For more details see e.g. Outokumpu data sheet for Duplex Stainless Steel and Outokumpu Corrosion Handbook.

Microstructure / Ferrite content

The balanced chemical composition of LDX 2101® results in a microstructure containing approximately equal amounts of ferrite and austenite after annealing at a temperature of about 1050°C. Due to its relatively low alloying content, LDX 2101® is less prone to precipitation of intermetallic phases than other Duplex steels. The high

nitrogen content results in rapid reformation of austenite when welding. By determining the ferrite content in the weld, it is ensured that the welding and/or annealing has been done properly. The general opinion is that a too high ferrite content, i.e. > 70% decreases the toughness and pitting resistance, and a too low ferrite content, i.e. < 25% decreases the SCC resistance.

Product Standards

Europe

- EN 10217-7: Welded steel tubes for pressure purposes – Technical delivery conditions Part 7: Stainless steel tubes
- EN 10296-2: Welded circular steel tubes for mechanical and general engineering purposes – Technical delivery conditions Part 2: Stainless steel
- EN 10253-3: Butt-welding pipe fittings Part 3: Wrought austenitic and austenitic-ferritic (Duplex) stainless steels without specific inspection requirements.
- EN 10253-4: Butt-welding pipe fittings Part 4: Wrought austenitic and austenitic-ferritic (Duplex) stainless steels with specific inspection requirements.

Note: LDX 2101® (EN 1.4162) is not included in EN standards yet, but LDX 2101® is an established material to use in pressure applications. By referring to the EAM (European Approval for pressurised equipment Materials) LDX 2101® shows conformity with the Pressure Equipment Directive (PED).

USA

- ASTM A 789: Seamless and Welded Ferritic/Austenitic Stainless Steel Tubing for General Service
- ASTM A 790: Seamless and Welded Ferritic/Austenitic Stainless Steel Pipes
- ASTM A 928: Seamless and Welded Ferritic/Austenitic Stainless Steel Pipe electric fusion welded with addition of filler metal
- ASTM A 815: Wrought Ferritic, Ferritic/Austenitic, and Martensitic Stainless Steel Piping Fittings

Weld factor

Type of weld process and NDT	EN 13480-3		ASME B31		
	EN 10217-7 / EN 10253-4	EN 10296-2 / EN 10253-3	A 789	A 790	A 928
EFW, 100% ET	1.0	-	0.8	0.8	0.8
EFW, 100% RT	1.0	-	1.0	1.0	1.0
EFW, spot RT	-	0.85	-	-	0.9
EFW, double butt	-	0.7	0.85	0.85	0.85
EFW, single butt	-	0.7	0.8	0.8	-

EFW = Electric Fusion Welded ET = Eddy Current Test RT = Radiographic Test

The joint coefficient (z used in EN standards) or Joint quality factor (Ej, used in ASME standards) is used for calculation of the wall thickness for welded tubes. The type of welding process, amount and type of NDT decide the factor.

Chemical composition, % (Typical values)

Outokumpu	EN	ASME/UNS	C	Cr	Ni	Mo	N	Others	PRE*
4307	1.4307	304L	0.02	18.1	8.1	-	-	-	18
4404	1.4404	316L	0.02	17.2	10.1	2.1	-	-	24
LDX 2101®	1.4162	S32101	0.03	21.5	1.5	0.3	0.22	5Mn	26
2304	1.4362	S32304	0.02	23	4.8	0.3	0.10	-	26
LDX 2404™	1.4662	S82441	0.02	24	3.6	1.6	0.27	3Mn	33
2205	1.4462	S32205**	0.02	22	5.7	3.1	0.17	-	35
2507	1.4410	S32750	0.02	25	7	4	0.27	-	43

* PRE = % Cr + 3.3% Mo + 16% N (The formula is used as a ranking tool to estimate pitting corrosion resistance in the material).

** Also available as S31803.

Information given in this data sheet may be subject to alterations without notice. Care has been taken to ensure that the contents of this publication are accurate but OSTP and its affiliated companies do not accept responsibility for errors or for information that is found to be misleading. Suggestions for or descriptions of the end use or application of products or methods of working are for information only and OSTP and its affiliated companies accept no liability in respect thereof. Before using products supplied or manufactured by the company the customer should satisfy himself of their suitability. Technical and other data in this publication are typical and may not be regarded as guaranteed maximum or minimum values unless this is specifically stated.

Pressure vessel requirements

Europe

The Pressure Equipment Directive (PED) regulates the use of stainless steel pipe and fittings in most European countries. OSTP fulfils the Directive, and is an approved manufacturer of welded Duplex stainless tubular products.

Outside Europe

Pressure vessel regulations are authorized to ASME. ASME Section II, Part D Table 2A, shows design values for tube and pipe.

ASME B31.1 Power Piping and ASME B31.3 Process Piping state design for approved pipe material.

Fabrication

Welding

Common welding methods for tubular products are:

- MMA, SMAW (Shielded Metal Arc Welding)
- TIG, GTAW (Gas Tungsten Arc Welding)
- MIG, MAG, GMAW (Gas Metal Arc Welding)
- FCAW (Flux-Cored Arc Welding)
- PAW (Plasma Arc Welding)
- SAW (Submerged Arc Welding)

For TIG and PAW methods the general recommendation for shielding and plasma gas is pure Ar. An addition of 1–2% N₂ in the shielding gas will improve the corrosion resistance in the weld. As backing/purging gas the general recommendation is Formier gas (90% N₂ and 10% H₂), pure Argon could also be used but the addition of nitrogen enhances the corrosion resistance of the weld. When material thickness requires more than one run, the interpass temperature has to be below 150°C. General filler recommendation for Duplex steel grade LDX 2101® can be found in the table below. Welding without filler metal not followed by post-weld heat treatment might reduce the corrosion resistance. Welding against other steel grades is also possible when suitable filler metal and shielding/backing gas is used. See Outokumpu Welding Handbook for more information.

Cold forming

Due to the high proof strength of Duplex material, greater working forces than those required for austenitic steel are usually needed for cold forming. LDX 2101® is suitable for most forming operations used in stainless steel fabrication. However, due to the grade's higher mechanical strength and lower toughness, operations such as expanding, bending, hydro forming or other forming methods are more demanding to perform than with austenitic steel. The grade's high mechanical strength, may

give rise to a relatively high spring back. For example during tube bending operations the minimum recommended bending radius is $\geq 2.5 \times OD$. However, this requires good quality bending machine, tooling and qualified operator.

Heat treatment

LDX 2101® is solution annealed at 1020–1080°C. Rapid cooling is recommended after annealing.

Applications

- Welded pipe systems within:
 - Pulp and Paper
 - Chemical and Petrochemical
 - Water Treatment
- Transportation
- Architecture, Building and Construction
- Heat exchanger tubes

"LDX 2101® has passed all test procedures require to permit approval for use in the UK water supply."

Design

Please use our Pressure Calculation Tool on www.ostp.biz, to discover the weight saving possibilities and other benefits of Outokumpu Duplex stainless steel.

General filler recommendation for Duplex stainless steels

Outokumpu	EN	ASTM / UNS	Welding consumables	
			Covered electrodes ISO 3581 / ISO 14172	Wires ISO 14343 / ISO 18274
LDX 2101®	1.4162	S32101	23 7 NL or 22 9 3 NL	23 7 NL or 22 9 3 NL
2304	1.4362	S32304	23 7 NL or 22 9 3 NL	23 7 NL or 22 9 3 NL
LDX 2404™	1.4662	S82441	22 9 3 NL	22 9 3 NL
2205	1.4462	S2205 / S31803	22 9 3 NL	22 9 3 NL
2507	1.4410	S32750	25 9 4 NL	25 9 4 NL

Mechanical properties (At room temperature)

Outokumpu	Min values acc. to EN 10028-7:2007									Min values according to ASTM A240-10		
	R _{p0.2} , MPa			R _m , MPa			A ₈₀ , %			R _{p0.2} , MPa	R _m , MPa	A ₅ , %
	P	H	C	P	H	C	P	H	C			
4307	200	200	220	500	520	520	45	45	45	170	485	40
4404	220	220	240	520	530	530	45	40	40	170	485	40
LDX 2101®	450*	465*	515*	650*	680*	700*	30*	30*	25/30*	530 (t \geq 5.0 mm) / 450 (t > 5.0 mm)	700 (t \leq 5.0 mm) / 650 (t > 5.0 mm)	30
2304	385/400	385/400	405/420	630	600	600	25	20	20	400	600	25
LDX 2404™	480**	550**	550**	680**	750**	750**	25**	25**	25/20**	540 (t < 10 mm) / 480 (t \geq 10 mm)	740 (t < 10 mm) / 680 (t \geq 10 mm)	25
2205	445/460	445/460	485/500	640	700	700	25	25	20	450	655	25
2507	515/530	515/530	535/550	730	750	750	20	20	20	550	795	15

* Min values according to EAM-0045-01:2012/01 ** Min values from internal standard AM641E Ed.2

P = Hot rolled plate H = Hot rolled strip C = Cold rolled coil and strip

For hot rolled plate (P) with T = 4.76 – 75 mm the impact toughness in transverse direction for LDX 2101® = 60 Joule at 20°C and 27 Joule at -40°C (values from internal standard AM 611E). For hot rolled strip (H) and cold rolled coil and strip (C) with T \leq 10 mm the impact toughness in transverse direction for LDX 2101® = 80 Joule at 20°C and 50 Joule at -40°C according to EAM-0045-01:2012/01.

Physical properties

Outokumpu	Density, g/cm ³	Modulus of elasticity, GPa	Poisson's ratio $\nu = -\epsilon_{trans} / \epsilon_{longitudinal}$	Average linear expansion at RT - 100°C x 10 ⁻⁶ / °C
4307	7.9	200	0.3	16.0
4404	8.0	200	0.3	16.0
LDX 2101®	7.8	200	0.3	13.0
2304	7.8	200	0.3	13.0
LDX 2404™	7.7	205	0.3*	13.0
2205	7.8	200	0.3	13.0
2507	7.8	200	0.3	13.0

* 0.3 is the typical Duplex value. Grade specific value are in the process of being established for LDX 2404™.

Information given in this data sheet may be subject to alterations without notice. Care has been taken to ensure that the contents of this publication are accurate but OSTP and its affiliated companies do not accept responsibility for errors or for information that is found to be misleading. Suggestions for or descriptions of the end use or application of products or methods of working are for information only and OSTP and its affiliated companies accept no liability in respect thereof. Before using products supplied or manufactured by the company the customer should satisfy himself of their suitability. Technical and other data in this publication are typical and may not be regarded as guaranteed maximum or minimum values unless this is specifically stated.

OSTP is a joint-venture between Tubinoxia and Outokumpu Group. OSTP manufactures the broadest range of stainless steel tubular products:

PROCESS PIPES

- Jakobstad, Finland
- Riyadh, Saudi Arabia

HEAVY WALL PIPES

- Storfors, Sweden

BUTT WELDED FITTINGS

- Örnsköldsvik, Sweden
- Jakobstad, Finland

PROCESS EQUIPMENT

- ÖMV, Örnsköldsvik, Sweden

OSTP

www.ostp.biz