

OSTP

OSTP AAF for welded tubes & pipes - December 2021

			Currency / Kgs				Old Ref			
EN	ASTM	OSTP	EUR	GBP	USD	SEK	GRADE	CR	NI	MO
1.4301	304	4301	2.677	2.270	3.088	26.686	17-9	18.0	8-9	
1.4307	304L	4307	2.677	2.270	3.088	26.686	18-8L	18.0	8-9	
1.4306	304L	4306	2.952	2.504	3.406	29.436	18-10L	18.0	10.0	
1.4541	321	4541	2.922	2.478	3.371	29.129	18-10Ti	17.0	9.0	
1.4401	316	4401	4.113	3.489	4.746	41.011	17-11-2	16.5	10.0	2.0
1.4404	316L	4404	4.113	3.489	4.746	41.011	17-11-2L	16.5	10.0	2.0
1.4571	316Ti	4571	4.175	3.540	4.815	41.614	17-11-2Ti	16.5	10.5	2.0
1.4436	316	4436	4.453	3.777	5.138	44.394	17-11-2.5	16.5	10.5	2.5
1.4432	316L	4432	4.503	3.819	5.194	44.891	17-12-2.5L	16.5	10.5	2.5
1.4435	316L	4435	4.617	3.916	5.327	46.026	17-13-2.5L	17.0	12.5	2.5
1.4438	317L	4438	5.247	4.450	6.052	52.300	18-13-3L	18.0	13.0	3.0
1.4818	S30415	153MA	2.750	2.333	3.173	27.421	153MA™	18.5	9.5	
1.4845	310S	4845	4.809	4.079	5.548	47.944	25-20	25.0	20.0	
1.4833	309S	4833	3.582	3.038	4.132	35.707	23-13	22.0	12.5	
1.4835	S30815	253MA	3.159	2.678	3.644	31.491	253MA®	21.0	11.0	
1.4539	904L	904L	7.385	6.263	8.519	73.617	904L	20.0	25.0	4.0
1.4547	S31254	254 SMO	7.038	5.968	8.119	70.160	254SMO®	20.0	18.0	6.0
1.4652	S32654	654 SMO	8.386	7.111	9.673	83.592	654 SMO®	24.0	22.0	7.3
1.4362	S32304	2304	2.607	2.210	3.007	25.979	2304	23.0	4.5	
1.4462	S31803	2205	3.640	3.087	4.199	36.285	2205	22.0	5.5	3.0
1.4410	S32750	2507	4.270	3.620	4.925	42.562	2507	25.0	7.0	4.0
1.4162	S32101	LDX2101	2.104	1.784	2.428	20.976	LDX2101®	21.0	1.5	
1.4828	-	4828	3.446	2.923	3.976	34.362	20-12Si	20.0	12.0	
1.4662	S82441	LDX2404	2.950	2.501	3.402	29.404	LDX2404™			
1.4003	S40977	4003	1.060	0.899	1.223	10.566	Ferritic			
1.4016	430	4016	1.197	1.015	1.380	11.928	Ferritic			
1.4509	441	4509	1.433	1.215	1.652	14.276	Ferritic			
1.4512	409	4512	1.016	0.862	1.172	10.128	Ferritic			
1.4521	444	4521	2.202	1.868	2.540	21.952	Ferritic			