

OSTP

OSTP AAF for welded tubes & pipes - June 2022

			Currency / Kgs				Old Ref			
EN	ASTM	OSTP	EUR	GBP	USD	SEK	GRADE	CR	NI	MO
1.4301	304	4301	3.734	3.156	3.947	38.920	17-9	18.0	8-9	
1.4307	304L	4307	3.734	3.156	3.947	38.920	18-8L	18.0	8-9	
1.4306	304L	4306	4.134	3.494	4.370	43.082	18-10L	18.0	10.0	
1.4541	321	4541	4.135	3.496	4.371	43.099	18-10Ti	17.0	9.0	
1.4401	316	4401	5.500	4.649	5.814	57.317	17-11-2	16.5	10.0	2.0
1.4404	316L	4404	5.500	4.649	5.814	57.317	17-11-2L	16.5	10.0	2.0
1.4571	316Ti	4571	5.633	4.762	5.954	58.711	17-11-2Ti	16.5	10.5	2.0
1.4436	316	4436	5.921	5.005	6.258	61.705	17-11-2.5	16.5	10.5	2.5
1.4432	316L	4432	5.958	5.037	6.298	62.092	17-12-2.5L	16.5	10.5	2.5
1.4435	316L	4435	6.160	5.207	6.511	64.193	17-13-2.5L	17.0	12.5	2.5
1.4438	317L	4438	6.965	5.887	7.361	72.581	18-13-3L	18.0	13.0	3.0
1.4818	S30415	153MA	3.808	3.219	4.025	39.688	153MA™	18.5	9.5	
1.4845	310S	4845	6.822	5.766	7.211	71.098	25-20	25.0	20.0	
1.4833	309S	4833	5.038	4.258	5.326	52.502	23-13	22.0	12.5	
1.4835	S30815	253MA	4.403	3.722	4.655	45.894	253MA®	21.0	11.0	
1.4539	904L	904L	9.891	8.361	10.456	103.089	904L	20.0	25.0	4.0
1.4547	S31254	254 SMO	9.106	7.698	9.626	94.903	254SMO®	20.0	18.0	6.0
1.4652	S32654	654 SMO	10.696	9.042	11.307	111.478	654 SMO®	24.0	22.0	7.3
1.4362	S32304	2304	3.398	2.872	3.591	35.408	2304	23.0	4.5	
1.4462	S31803	2205	4.652	3.932	4.917	48.476	2205	22.0	5.5	3.0
1.4410	S32750	2507	5.413	4.575	5.721	56.408	2507	25.0	7.0	4.0
1.4162	S32101	LDX2101	2.428	2.052	2.566	25.303	LDX2101®	21.0	1.5	
1.4828	-	4828	4.823	4.077	5.098	50.265	20-12Si	20.0	12.0	
1.4662	S82441	LDX2404	3.613	3.054	3.819	37.655	LDX2404™			
1.4003	S40977	4003	1.398	1.182	1.478	14.572	Ferritic			
1.4016	430	4016	1.575	1.332	1.666	16.423	Ferritic			
1.4509	441	4509	1.817	1.536	1.920	18.934	Ferritic			
1.4512	409	4512	1.361	1.151	1.438	14.180	Ferritic			
1.4521	444	4521	2.718	2.297	2.872	28.321	Ferritic			