

OSTP

OSTP AAF for welded tubes & pipes - Oct 2022

			Currency / Kgs				Old Ref			
EN	ASTM	OSTP	EUR	GBP	USD	SEK	GRADE	CR	NI	MO
1.4301	304	4301	3.068	2.638	3.065	32.725	17-9	18.0	8-9	
1.4307	304L	4307	3.068	2.638	3.065	32.725	18-8L	18.0	8-9	
1.4306	304L	4306	3.432	2.951	3.429	36.614	18-10L	18.0	10.0	
1.4541	321	4541	3.421	2.942	3.417	36.490	18-10Ti	17.0	9.0	
1.4401	316	4401	4.641	3.990	4.637	49.500	17-11-2	16.5	10.0	2.0
1.4404	316L	4404	4.641	3.990	4.637	49.500	17-11-2L	16.5	10.0	2.0
1.4571	316Ti	4571	4.741	4.076	4.736	50.570	17-11-2Ti	16.5	10.5	2.0
1.4436	316	4436	5.007	4.305	5.002	53.404	17-11-2.5	16.5	10.5	2.5
1.4432	316L	4432	5.046	4.338	5.041	53.824	17-12-2.5L	16.5	10.5	2.5
1.4435	316L	4435	5.201	4.472	5.197	55.485	17-13-2.5L	17.0	12.5	2.5
1.4438	317L	4438	5.895	5.068	5.889	62.874	18-13-3L	18.0	13.0	3.0
1.4818	S30415	153MA	3.181	2.734	3.177	33.928	153MA™	18.5	9.5	
1.4845	310S	4845	5.657	4.864	5.652	60.337	25-20	25.0	20.0	
1.4833	309S	4833	4.188	3.601	4.184	44.669	23-13	22.0	12.5	
1.4835	S30815	253MA	3.652	3.139	3.648	38.949	253MA®	21.0	11.0	
1.4539	904L	904L	8.336	7.166	8.328	88.912	904L	20.0	25.0	4.0
1.4547	S31254	254 SMO	7.779	6.687	7.771	82.968	254SMO®	20.0	18.0	6.0
1.4652	S32654	654 SMO	9.129	7.849	9.120	97.374	654 SMO®	24.0	22.0	7.3
1.4362	S32304	2304	2.871	2.468	2.869	30.625	2304	23.0	4.5	
1.4462	S31803	2205	4.010	3.448	4.005	42.768	2205	22.0	5.5	3.0
1.4410	S32750	2507	4.691	4.032	4.686	50.031	2507	25.0	7.0	4.0
1.4162	S32101	LDX2101	2.057	1.768	2.054	21.938	LDX2101®	21.0	1.5	
1.4828	-	4828	3.985	3.427	3.981	42.506	20-12Si	20.0	12.0	
1.4662	S82441	LDX2404	3.094	2.660	3.091	33.004	LDX2404™			
1.4003	S40977	4003	1.167	1.003	1.166	12.448	Ferritic			
1.4016	430	4016	1.339	1.151	1.337	14.281	Ferritic			
1.4509	441	4509	1.568	1.349	1.567	16.733	Ferritic			
1.4512	409	4512	1.134	0.976	1.133	12.102	Ferritic			
1.4521	444	4521	2.383	2.049	2.380	25.419	Ferritic			