

OSTP

OSTP AAF for welded tubes & pipes - Sep 2023

			Currency / Kgs				Old Ref			
EN	ASTM	OSTP	EUR	GBP	USD	SEK	GRADE	CR	NI	MO
1.4301	304	4301	2.520	2.169	2.768	29.393	17-9	18.0	8-9	
1.4307	304L	4307	2.520	2.169	2.768	29.393	18-8L	18.0	8-9	
1.4306	304L	4306	2.789	2.401	3.065	32.542	18-10L	18.0	10.0	
1.4541	321	4541	2.757	2.374	3.029	32.163	18-10Ti	17.0	9.0	
1.4401	316	4401	4.279	3.683	4.702	49.924	17-11-2	16.5	10.0	2.0
1.4404	316L	4404	4.279	3.683	4.702	49.924	17-11-2L	16.5	10.0	2.0
1.4571	316Ti	4571	4.336	3.733	4.764	50.583	17-11-2Ti	16.5	10.5	2.0
1.4436	316	4436	4.690	4.038	5.153	54.716	17-11-2.5	16.5	10.5	2.5
1.4432	316L	4432	4.777	4.114	5.250	55.743	17-12-2.5L	16.5	10.5	2.5
1.4435	316L	4435	4.850	4.176	5.329	56.587	17-13-2.5L	17.0	12.5	2.5
1.4438	317L	4438	5.583	4.807	6.135	65.144	18-13-3L	18.0	13.0	3.0
1.4818	S30415	153MA	2.598	2.237	2.854	30.311	153MA™	18.5	9.5	
1.4845	310S	4845	4.608	3.968	5.065	53.772	25-20	25.0	20.0	
1.4833	309S	4833	3.404	2.930	3.740	39.713	23-13	22.0	12.5	
1.4835	S30815	253MA	2.956	2.544	3.248	34.479	253MA®	21.0	11.0	
1.4539	904L	904L	7.820	6.733	8.593	91.241	904L	20.0	25.0	4.0
1.4547	S31254	254 SMO	7.797	6.713	8.568	90.967	254SMO®	20.0	18.0	6.0
1.4652	S32654	654 SMO	9.100	7.835	9.999	106.173	654 SMO®	24.0	22.0	7.3
1.4362	S32304	2304	2.436	2.096	2.676	28.413	2304	23.0	4.5	
1.4462	S31803	2205	3.962	3.411	4.354	46.224	2205	22.0	5.5	3.0
1.4410	S32750	2507	4.732	4.074	5.199	55.209	2507	25.0	7.0	4.0
1.4162	S32101	LDX2101	1.748	1.505	1.921	20.396	LDX2101®	21.0	1.5	
1.4828	-	4828	3.229	2.780	3.549	37.675	20-12Si	20.0	12.0	
1.4662	S82441	LDX2404	2.861	2.463	3.144	33.387	LDX2404™			
1.4003	S40977	4003	0.938	0.807	1.030	10.942	Ferritic			
1.4016	430	4016	1.070	0.920	1.175	12.475	Ferritic			
1.4509	441	4509	1.343	1.157	1.477	15.673	Ferritic			
1.4512	409	4512	0.892	0.768	0.981	10.413	Ferritic			
1.4521	444	4521	2.437	2.099	2.678	28.438	Ferritic			