

# OSTP

AAF / Alloy Adjustment Factor

AAF for welded tubes and pipes - March 2025										
			Currency / Kgs				Old Ref			
EN	ASTM	OSTP	EUR	GBP	USD	SEK	GRADE	CR	NI	MO
1.4301	304	4301	2,416	2,021	2,513	27,485	17-9	18,0	8-9	
1.4307	304L	4307	2,416	2,021	2,513	27,485	18-8L	18,0	8-9	
1.4306	304L	4306	2,644	2,211	2,750	30,073	18-10L	18,0	10,0	
1.4541	321	4541	2,613	2,185	2,717	29,716	18-10Ti	17,0	9,0	
1.4401	316	4401	4,007	3,351	4,166	45,569	17-11-2	16,5	10,0	2,0
1.4404	316L	4404	4,007	3,351	4,166	45,569	17-11-2L	16,5	10,0	2,0
1.4571	316Ti	4571	4,054	3,390	4,216	46,107	17-11-2Ti	16,5	10,5	2,0
1.4436	316	4436	4,377	3,660	4,552	49,782	17-11-2.5	16,5	10,5	2,5
1.4432	316L	4432	4,463	3,732	4,641	50,758	17-12-2.5L	16,5	10,5	2,5
1.4435	316L	4435	4,510	3,772	4,691	51,292	17-13-2.5L	17,0	12,5	2,5
1.4438	317L	4438	5,165	4,319	5,372	58,745	18-13-3L	18,0	13,0	3,0
1.4818	S30415	153MA	2,485	2,078	2,584	28,259	153MA™	18,5	9,5	
1.4845	310S	4845	4,180	3,496	4,348	47,549	25-20	25,0	20,0	
1.4833	309S	4833	3,172	2,652	3,298	36,072	23-13	22,0	12,5	
1.4835	S30815	253MA	2,791	2,335	2,903	31,748	253MA®	21,0	11,0	
1.4539	904L	904L	7,115	5,950	7,400	80,929	904L	20,0	25,0	4,0
1.4547	S31254	254 SMO	7,201	6,023	7,490	81,909	254SMO®	20,0	18,0	6,0
1.4652	S32654	654 SMO	8,346	6,979	8,679	94,914	654 SMO®	24,0	22,0	7,3
1.4362	S32304	2304	2,415	2,019	2,512	27,461	2304	23,0	4,5	
1.4462	S31803	2205	3,826	3,199	3,979	43,516	2205	22,0	5,5	3,0
1.4410	S32750	2507	4,540	3,797	4,722	51,644	2507	25,0	7,0	4,0
1.4162	S32101	LDX2101	1,848	1,546	1,922	21,015	LDX2101®	21,0	1,5	
1.4828	-	4828	3,039	2,543	3,161	34,572	20-12Si	20,0	12,0	
1.4662	S82441	LDX2404	2,837	2,372	2,950	32,262	LDX2404™			
1.4003	S40977	4003	1,089	0,911	1,132	12,380	Ferritic			
1.4016	430	4016	1,227	1,026	1,277	13,953	Ferritic			
1.4509	441	4509	1,541	1,288	1,602	17,521	Ferritic			
1.4512	409	4512	1,044	0,873	1,087	11,878	Ferritic			
1.4521	444	4521	2,542	2,125	2,643	28,901	Ferritic			