

OSTP

AAF / Alloy Adjustment Factor

AAF for welded tubes and pipes - May 2025										
			Currency / Kgs				Old Ref			
EN	ASTM	OSTP	EUR	GBP	USD	SEK	GRADE	CR	NI	MO
1.4301	304	4301	2,282	1,932	2,514	24,971	17-9	18,0	8-9	
1.4307	304L	4307	2,282	1,932	2,514	24,971	18-8L	18,0	8-9	
1.4306	304L	4306	2,493	2,111	2,747	27,293	18-10L	18,0	10,0	
1.4541	321	4541	2,463	2,086	2,714	26,962	18-10Ti	17,0	9,0	
1.4401	316	4401	3,751	3,177	4,133	41,060	17-11-2	16,5	10,0	2,0
1.4404	316L	4404	3,751	3,177	4,133	41,060	17-11-2L	16,5	10,0	2,0
1.4571	316Ti	4571	3,794	3,213	4,179	41,524	17-11-2Ti	16,5	10,5	2,0
1.4436	316	4436	4,094	3,467	4,510	44,810	17-11-2.5	16,5	10,5	2,5
1.4432	316L	4432	4,172	3,534	4,597	45,670	17-12-2.5L	16,5	10,5	2,5
1.4435	316L	4435	4,218	3,572	4,647	46,168	17-13-2.5L	17,0	12,5	2,5
1.4438	317L	4438	4,825	4,086	5,315	52,807	18-13-3L	18,0	13,0	3,0
1.4818	S30415	153MA	2,344	1,985	2,582	25,650	153MA™	18,5	9,5	
1.4845	310S	4845	3,926	3,325	4,325	42,970	25-20	25,0	20,0	
1.4833	309S	4833	2,984	2,527	3,288	32,661	23-13	22,0	12,5	
1.4835	S30815	253MA	2,631	2,228	2,898	28,794	253MA®	21,0	11,0	
1.4539	904L	904L	6,645	5,627	7,321	72,727	904L	20,0	25,0	4,0
1.4547	S31254	254 SMO	6,709	5,681	7,391	73,425	254SMO®	20,0	18,0	6,0
1.4652	S32654	654 SMO	7,767	6,577	8,556	85,008	654 SMO®	24,0	22,0	7,3
1.4362	S32304	2304	2,274	1,925	2,505	24,880	2304	23,0	4,5	
1.4462	S31803	2205	3,574	3,027	3,938	39,122	2205	22,0	5,5	3,0
1.4410	S32750	2507	4,234	3,586	4,664	46,339	2507	25,0	7,0	4,0
1.4162	S32101	LDX2101	1,749	1,481	1,926	19,139	LDX2101®	21,0	1,5	
1.4828	-	4828	2,866	2,428	3,158	31,371	20-12Si	20,0	12,0	
1.4662	S82441	LDX2404	2,660	2,252	2,930	29,107	LDX2404™			
1.4003	S40977	4003	1,045	0,884	1,151	11,437	Ferritic			
1.4016	430	4016	1,170	0,990	1,289	12,803	Ferritic			
1.4509	441	4509	1,484	1,256	1,634	16,230	Ferritic			
1.4512	409	4512	1,002	0,848	1,103	10,957	Ferritic			
1.4521	444	4521	2,397	2,030	2,640	26,232	Ferritic			