

OSTP

AAF / Alloy Adjustment Factor

AAF for welded tubes and pipes - September 2025										
			Currency / Kgs				Old Ref			
EN	ASTM	OSTP	EUR	GBP	USD	SEK	GRADE	CR	NI	MO
1.4301	304	4301	2,167	1,876	2,521	24,216	17-9	18,0	8-9	
1.4307	304L	4307	2,167	1,876	2,521	24,216	18-8L	18,0	8-9	
1.4306	304L	4306	2,314	2,003	2,692	25,861	18-10L	18,0	10,0	
1.4541	321	4541	2,338	2,024	2,721	26,134	18-10Ti	17,0	9,0	
1.4401	316	4401	3,681	3,187	4,284	41,147	17-11-2	16,5	10,0	2,0
1.4404	316L	4404	3,681	3,187	4,284	41,147	17-11-2L	16,5	10,0	2,0
1.4571	316Ti	4571	3,721	3,222	4,331	41,601	17-11-2Ti	16,5	10,5	2,0
1.4436	316	4436	3,968	3,436	4,618	44,357	17-11-2.5	16,5	10,5	2,5
1.4432	316L	4432	4,057	3,513	4,722	45,355	17-12-2.5L	16,5	10,5	2,5
1.4435	316L	4435	4,080	3,533	4,748	45,609	17-13-2.5L	17,0	12,5	2,5
1.4438	317L	4438	4,686	4,058	5,454	52,393	18-13-3L	18,0	13,0	3,0
1.4818	S30415	153MA	2,176	1,884	2,531	24,318	153MA™	18,5	9,5	
1.4845	310S	4845	3,724	3,225	4,334	41,635	25-20	25,0	20,0	
1.4833	309S	4833	2,765	2,394	3,218	30,907	23-13	22,0	12,5	
1.4835	S30815	253MA	2,444	2,116	2,844	27,314	253MA®	21,0	11,0	
1.4539	904L	904L	6,419	5,559	7,472	71,765	904L	20,0	25,0	4,0
1.4547	S31254	254 SMO	6,627	5,739	7,713	74,090	254SMO®	20,0	18,0	6,0
1.4652	S32654	654 SMO	7,665	6,638	8,921	85,692	654 SMO®	24,0	22,0	7,3
1.4362	S32304	2304	2,171	1,880	2,528	24,277	2304	23,0	4,5	
1.4462	S31803	2205	3,543	3,068	4,124	39,609	2205	22,0	5,5	3,0
1.4410	S32750	2507	4,209	3,644	4,898	47,050	2507	25,0	7,0	4,0
1.4162	S32101	LDX2101	1,691	1,464	1,968	18,901	LDX2101®	21,0	1,5	
1.4828	-	4828	2,655	2,299	3,090	29,684	20-12Si	20,0	12,0	
1.4662	S82441	LDX2404	2,611	2,260	3,038	29,180	LDX2404™			
1.4003	S40977	4003	1,009	0,873	1,174	11,275	Ferritic			
1.4016	430	4016	1,135	0,983	1,321	12,694	Ferritic			
1.4509	441	4509	1,432	1,240	1,666	16,006	Ferritic			
1.4512	409	4512	0,953	0,825	1,109	10,651	Ferritic			
1.4521	444	4521	2,406	2,083	2,799	26,892	Ferritic			