

OSTP

AAF / Alloy Adjustment Factor

AAF for welded tubes and pipes - October 2025										
			Currency / Kgs				Old Ref			
EN	ASTM	OSTP	EUR	GBP	USD	SEK	GRADE	CR	NI	MO
1.4301	304	4301	2,167	1,877	2,536	23,911	17-9	18,0	8-9	
1.4307	304L	4307	2,167	1,877	2,536	23,911	18-8L	18,0	8-9	
1.4306	304L	4306	2,316	2,006	2,709	25,556	18-10L	18,0	10,0	
1.4541	321	4541	2,340	2,026	2,738	25,819	18-10Ti	17,0	9,0	
1.4401	316	4401	3,763	3,259	4,403	41,524	17-11-2	16,5	10,0	2,0
1.4404	316L	4404	3,763	3,259	4,403	41,524	17-11-2L	16,5	10,0	2,0
1.4571	316Ti	4571	3,803	3,294	4,451	41,969	17-11-2Ti	16,5	10,5	2,0
1.4436	316	4436	4,069	3,524	4,760	44,894	17-11-2.5	16,5	10,5	2,5
1.4432	316L	4432	4,166	3,608	4,875	45,970	17-12-2.5L	16,5	10,5	2,5
1.4435	316L	4435	4,181	3,621	4,893	46,144	17-13-2.5L	17,0	12,5	2,5
1.4438	317L	4438	4,817	4,171	5,636	53,150	18-13-3L	18,0	13,0	3,0
1.4818	S30415	153MA	2,177	1,885	2,547	24,020	153MA™	18,5	9,5	
1.4845	310S	4845	3,740	3,238	4,376	41,261	25-20	25,0	20,0	
1.4833	309S	4833	2,772	2,400	3,242	30,575	23-13	22,0	12,5	
1.4835	S30815	253MA	2,446	2,118	2,862	26,993	253MA®	21,0	11,0	
1.4539	904L	904L	6,598	5,713	7,719	72,798	904L	20,0	25,0	4,0
1.4547	S31254	254 SMO	6,866	5,946	8,033	75,751	254SMO®	20,0	18,0	6,0
1.4652	S32654	654 SMO	7,942	6,877	9,292	87,633	654 SMO®	24,0	22,0	7,3
1.4362	S32304	2304	2,186	1,893	2,558	24,122	2304	23,0	4,5	
1.4462	S31803	2205	3,648	3,159	4,269	40,252	2205	22,0	5,5	3,0
1.4410	S32750	2507	4,345	3,763	5,083	47,939	2507	25,0	7,0	4,0
1.4162	S32101	LDX2101	1,697	1,470	1,986	18,730	LDX2101®	21,0	1,5	
1.4828	-	4828	2,661	2,305	3,113	29,363	20-12Si	20,0	12,0	
1.4662	S82441	LDX2404	2,662	2,306	3,115	29,379	LDX2404™			
1.4003	S40977	4003	0,999	0,865	1,168	11,023	Ferritic			
1.4016	430	4016	1,125	0,974	1,316	12,409	Ferritic			
1.4509	441	4509	1,420	1,231	1,662	15,675	Ferritic			
1.4512	409	4512	0,942	0,815	1,102	10,394	Ferritic			
1.4521	444	4521	2,466	2,134	2,884	27,200	Ferritic			