

OSTP

AAF / Alloy Adjustment Factor

AAF for welded tubes and pipes - November 2025										
			Currency / Kgs				Old Ref			
EN	ASTM	OSTP	EUR	GBP	USD	SEK	GRADE	CR	NI	MO
1.4301	304	4301	2,202	1,918	2,575	24,257	17-9	18,0	8-9	
1.4307	304L	4307	2,202	1,918	2,575	24,257	18-8L	18,0	8-9	
1.4306	304L	4306	2,355	2,052	2,754	25,951	18-10L	18,0	10,0	
1.4541	321	4541	2,378	2,071	2,781	26,198	18-10Ti	17,0	9,0	
1.4401	316	4401	3,772	3,286	4,410	41,558	17-11-2	16,5	10,0	2,0
1.4404	316L	4404	3,772	3,286	4,410	41,558	17-11-2L	16,5	10,0	2,0
1.4571	316Ti	4571	3,812	3,321	4,457	42,003	17-11-2Ti	16,5	10,5	2,0
1.4436	316	4436	4,072	3,547	4,761	44,862	17-11-2.5	16,5	10,5	2,5
1.4432	316L	4432	4,165	3,628	4,869	45,885	17-12-2.5L	16,5	10,5	2,5
1.4435	316L	4435	4,188	3,648	4,897	46,140	17-13-2.5L	17,0	12,5	2,5
1.4438	317L	4438	4,816	4,195	5,632	53,068	18-13-3L	18,0	13,0	3,0
1.4818	S30415	153MA	2,217	1,931	2,592	24,426	153MA™	18,5	9,5	
1.4845	310S	4845	3,810	3,319	4,455	41,981	25-20	25,0	20,0	
1.4833	309S	4833	2,821	2,458	3,298	31,080	23-13	22,0	12,5	
1.4835	S30815	253MA	2,486	2,165	2,906	27,388	253MA®	21,0	11,0	
1.4539	904L	904L	6,616	5,763	7,736	72,896	904L	20,0	25,0	4,0
1.4547	S31254	254 SMO	6,831	5,950	7,988	75,265	254SMO®	20,0	18,0	6,0
1.4652	S32654	654 SMO	7,906	6,887	9,245	87,109	654 SMO®	24,0	22,0	7,3
1.4362	S32304	2304	2,209	1,924	2,583	24,340	2304	23,0	4,5	
1.4462	S31803	2205	3,629	3,161	4,244	39,981	2205	22,0	5,5	3,0
1.4410	S32750	2507	4,322	3,764	5,053	47,615	2507	25,0	7,0	4,0
1.4162	S32101	LDX2101	1,712	1,492	2,002	18,870	LDX2101®	21,0	1,5	
1.4828	-	4828	2,705	2,355	3,163	29,797	20-12Si	20,0	12,0	
1.4662	S82441	LDX2404	2,666	2,322	3,117	29,365	LDX2404™			
1.4003	S40977	4003	1,006	0,876	1,176	11,087	Ferritic			
1.4016	430	4016	1,135	0,988	1,327	12,501	Ferritic			
1.4509	441	4509	1,431	1,247	1,673	15,763	Ferritic			
1.4512	409	4512	0,948	0,826	1,109	10,447	Ferritic			
1.4521	444	4521	2,444	2,129	2,858	26,923	Ferritic			