

OSTP

AAF / Alloy Adjustment Factor

AAF for welded tubes and pipes - December 2025										
			Currency / Kgs				Old Ref			
EN	ASTM	OSTP	EUR	GBP	USD	SEK	GRADE	CR	NI	MO
1.4301	304	4301	2,225	1,953	2,577	24,379	26,01875	18,0	8-9	
1.4307	304L	4307	2,225	1,953	2,577	24,379	26,01875	18,0	8-9	
1.4306	304L	4306	2,379	2,088	2,757	26,074	27,8277	18,0	10,0	
1.4541	321	4541	2,402	2,108	2,782	26,319	28,08875	17,0	9,0	
1.4401	316	4401	3,778	3,317	4,376	41,395	44,1784	16,5	10,0	2,0
1.4404	316L	4404	3,778	3,317	4,376	41,395	44,1784	16,5	10,0	2,0
1.4571	316Ti	4571	3,819	3,352	4,423	41,842	44,65565	16,5	10,5	2,0
1.4436	316	4436	4,074	3,577	4,718	44,641	47,6422	16,5	10,5	2,5
1.4432	316L	4432	4,165	3,656	4,824	45,633	48,70135	16,5	10,5	2,5
1.4435	316L	4435	4,191	3,679	4,854	45,916	49,0038	17,0	12,5	2,5
1.4438	317L	4438	4,814	4,226	5,576	52,751	56,2971	18,0	13,0	3,0
1.4818	S30415	153MA	2,241	1,968	2,596	24,556	26,20735	18,5	9,5	
1.4845	310S	4845	3,841	3,372	4,449	42,085	44,91555	25,0	20,0	
1.4833	309S	4833	2,847	2,500	3,298	31,202	33,30055	22,0	12,5	
1.4835	S30815	253MA	2,510	2,203	2,908	27,508	29,35835	21,0	11,0	
1.4539	904L	904L	6,617	5,808	7,664	72,502	77,3766	20,0	25,0	4,0
1.4547	S31254	254 SMO	6,809	5,977	7,887	74,613	79,62945	20,0	18,0	6,0
1.4652	S32654	654 SMO	7,879	6,916	9,126	86,329	92,1357	24,0	22,0	7,3
1.4362	S32304	2304	2,231	1,957	2,584	24,440	26,08315	23,0	4,5	
1.4462	S31803	2205	3,626	3,182	4,200	39,727	42,39935	22,0	5,5	3,0
1.4410	S32750	2507	4,314	3,786	4,996	47,262	50,44015	25,0	7,0	4,0
1.4162	S32101	LDX2101	1,734	1,523	2,009	19,006	20,28485	21,0	1,5	
1.4828	-	4828	2,730	2,395	3,161	29,909	31,92055	20,0	12,0	
1.4662	S82441	LDX2404	2,677	2,351	3,102	29,337	31,3099			
1.4003	S40977	4003	1,024	0,899	1,186	11,219	11,9738			
1.4016	430	4016	1,153	1,013	1,336	12,641	13,49065			
1.4509	441	4509	1,450	1,273	1,680	15,891	16,95905			
1.4512	409	4512	0,966	0,848	1,119	10,583	11,2953			
1.4521	444	4521	2,446	2,147	2,832	26,800	28,60165			