

OSTP

AAF / Alloy Adjustment Factor

AAF for welded tubes and pipes - January 2026										
			Currency / Kgs				Old Ref			
EN	ASTM	OSTP	EUR	GBP	USD	SEK	GRADE	CR	NI	MO
1.4301	304	4301	2,207	1,934	2,570	24,172	26,01875	18,0	8-9	
1.4307	304L	4307	2,207	1,934	2,570	24,172	26,01875	18,0	8-9	
1.4306	304L	4306	2,356	2,065	2,744	25,808	27,8277	18,0	10,0	
1.4541	321	4541	2,378	2,085	2,769	26,050	28,08875	17,0	9,0	
1.4401	316	4401	3,656	3,205	4,257	40,051	44,1784	16,5	10,0	2,0
1.4404	316L	4404	3,656	3,205	4,257	40,051	44,1784	16,5	10,0	2,0
1.4571	316Ti	4571	3,695	3,240	4,303	40,481	44,65565	16,5	10,5	2,0
1.4436	316	4436	3,930	3,444	4,576	43,040	47,6422	16,5	10,5	2,5
1.4432	316L	4432	4,010	3,516	4,670	43,929	48,70135	16,5	10,5	2,5
1.4435	316L	4435	4,042	3,544	4,707	44,277	49,0038	17,0	12,5	2,5
1.4438	317L	4438	4,629	4,058	5,390	50,702	56,2971	18,0	13,0	3,0
1.4818	S30415	153MA	2,216	1,942	2,581	24,272	26,20735	18,5	9,5	
1.4845	310S	4845	3,781	3,315	4,403	41,425	44,91555	25,0	20,0	
1.4833	309S	4833	2,813	2,467	3,276	30,818	33,30055	22,0	12,5	
1.4835	S30815	253MA	2,489	2,182	2,898	27,262	29,35835	21,0	11,0	
1.4539	904L	904L	6,363	5,579	7,411	69,704	77,3766	20,0	25,0	4,0
1.4547	S31254	254 SMO	6,495	5,695	7,565	71,154	79,62945	20,0	18,0	6,0
1.4652	S32654	654 SMO	7,510	6,584	8,745	82,260	92,1357	24,0	22,0	7,3
1.4362	S32304	2304	2,206	1,934	2,569	24,165	26,08315	23,0	4,5	
1.4462	S31803	2205	3,489	3,059	4,063	38,218	42,39935	22,0	5,5	3,0
1.4410	S32750	2507	4,131	3,621	4,810	45,253	50,44015	25,0	7,0	4,0
1.4162	S32101	LDX2101	1,730	1,517	2,014	18,945	20,28485	21,0	1,5	
1.4828	-	4828	2,701	2,369	3,146	29,595	31,92055	20,0	12,0	
1.4662	S82441	LDX2404	2,612	2,290	3,042	28,611	31,3099			
1.4003	S40977	4003	1,036	0,909	1,206	11,346	11,9738			
1.4016	430	4016	1,167	1,024	1,359	12,785	13,49065			
1.4509	441	4509	1,464	1,283	1,705	16,037	16,95905			
1.4512	409	4512	0,979	0,859	1,141	10,726	11,2953			
1.4521	444	4521	2,375	2,082	2,765	26,010	28,60165			