

OSTP

AAF / Alloy Adjustment Factor

AAF for welded tubes and pipes - July										
			Currency / Kgs				Old Ref			
EN	ASTM	OSTP	EUR	GBP	USD	SEK	GRADE	CR	NI	MO
1.4301	304	4301	2,698	2,333	3,127	29,337	17-9	18,0	8-9	
1.4307	304L	4307	2,698	2,333	3,127	29,337	18-8L	18,0	8-9	
1.4306	304L	4306	2,915	2,520	3,379	31,689	18-10L	18,0	10,0	
1.4541	321	4541	2,937	2,539	3,404	31,931	18-10Ti	17,0	9,0	
1.4401	316	4401	4,718	4,079	5,468	51,295	17-11-2	16,5	10,0	2,0
1.4404	316L	4404	4,718	4,079	5,468	51,295	17-11-2L	16,5	10,0	2,0
1.4571	316Ti	4571	4,774	4,127	5,533	51,902	17-11-2Ti	16,5	10,5	2,0
1.4436	316	4436	5,122	4,428	5,936	55,681	17-11-2.5	16,5	10,5	2,5
1.4432	316L	4432	5,241	4,530	6,073	56,968	17-12-2.5L	16,5	10,5	2,5
1.4435	316L	4435	5,279	4,563	6,117	57,383	17-13-2.5L	17,0	12,5	2,5
1.4438	317L	4438	6,089	5,264	7,056	66,196	18-13-3L	18,0	13,0	3,0
1.4818	S30415	153MA	2,736	2,364	3,171	29,740	153MA™	18,5	9,5	
1.4845	310S	4845	4,789	4,139	5,549	52,055	25-20	25,0	20,0	
1.4833	309S	4833	3,510	3,035	4,068	38,159	23-13	22,0	12,5	
1.4835	S30815	253MA	3,069	2,654	3,557	33,371	253MA®	21,0	11,0	
1.4539	904L	904L	8,467	7,320	9,813	92,055	904L	20,0	25,0	4,0
1.4547	S31254	254 SMO	8,672	7,497	10,051	94,284	254SMO®	20,0	18,0	6,0
1.4652	S32654	654 SMO	10,068	8,704	11,668	109,456	654 SMO®	24,0	22,0	7,3
1.4362	S32304	2304	2,668	2,306	3,091	29,000	2304	23,0	4,5	
1.4462	S31803	2205	4,460	3,856	5,169	48,490	2205	22,0	5,5	3,0
1.4410	S32750	2507	5,339	4,616	6,188	58,046	2507	25,0	7,0	4,0
1.4162	S32101	LDX2101	2,027	1,753	2,349	22,035	LDX2101®	21,0	1,5	
1.4828	-	4828	3,386	2,927	3,924	36,809	20-12Si	20,0	12,0	
1.4662	S82441	LDX2404	3,241	2,801	3,756	35,234	LDX2404™			
1.4003	S40977	4003	1,145	0,990	1,327	12,455	Ferritic			
1.4016	430	4016	1,266	1,095	1,467	13,767	Ferritic			
1.4509	441	4509	1,587	1,372	1,839	17,251	Ferritic			
1.4512	409	4512	1,071	0,926	1,241	11,638	Ferritic			
1.4521	444	4521	2,889	2,498	3,348	31,408	Ferritic			