

OSTP

AAF / Alloy Adjustment Factor

AAF for welded tubes and pipes - October										
			Currency / Kgs				Old Ref			
EN	ASTM	OSTP	EUR	GBP	USD	SEK	GRADE	CR	NI	MO
1.4301	304	4301	2,516	2,157	2,920	28,058	17-9	18,0	8-9	
1.4307	304L	4307	2,516	2,157	2,920	28,058	18-8L	18,0	8-9	
1.4306	304L	4306	2,706	2,320	3,140	30,168	18-10L	18,0	10,0	
1.4541	321	4541	2,728	2,339	3,166	30,422	18-10Ti	17,0	9,0	
1.4401	316	4401	4,597	3,941	5,335	51,256	17-11-2	16,5	10,0	2,0
1.4404	316L	4404	4,597	3,941	5,335	51,256	17-11-2L	16,5	10,0	2,0
1.4571	316Ti	4571	4,647	3,985	5,394	51,822	17-11-2Ti	16,5	10,5	2,0
1.4436	316	4436	5,012	4,298	5,817	55,889	17-11-2.5	16,5	10,5	2,5
1.4432	316L	4432	5,147	4,414	5,974	57,401	17-12-2.5L	16,5	10,5	2,5
1.4435	316L	4435	5,151	4,416	5,978	57,432	17-13-2.5L	17,0	12,5	2,5
1.4438	317L	4438	5,967	5,118	6,926	66,547	18-13-3L	18,0	13,0	3,0
1.4818	S30415	153MA	2,545	2,182	2,953	28,375	153MA™	18,5	9,5	
1.4845	310S	4845	4,399	3,772	5,105	49,046	25-20	25,0	20,0	
1.4833	309S	4833	3,246	2,784	3,769	36,207	23-13	22,0	12,5	
1.4835	S30815	253MA	2,851	2,445	3,310	31,795	253MA®	21,0	11,0	
1.4539	904L	904L	8,234	7,060	9,557	91,815	904L	20,0	25,0	4,0
1.4547	S31254	254 SMO	8,665	7,430	10,057	96,625	254SMO®	20,0	18,0	6,0
1.4652	S32654	654 SMO	10,037	8,607	11,650	111,921	654 SMO®	24,0	22,0	7,3
1.4362	S32304	2304	2,586	2,217	3,002	28,837	2304	23,0	4,5	
1.4462	S31803	2205	4,500	3,859	5,223	50,184	2205	22,0	5,5	3,0
1.4410	S32750	2507	5,398	4,629	6,265	60,198	2507	25,0	7,0	4,0
1.4162	S32101	LDX2101	2,004	1,719	2,326	22,353	LDX2101®	21,0	1,5	
1.4828	-	4828	3,148	2,699	3,654	35,105	20-12Si	20,0	12,0	
1.4662	S82441	LDX2404	3,245	2,783	3,767	36,192	LDX2404™			
1.4003	S40977	4003	1,117	0,957	1,296	12,448	Ferritic			
1.4016	430	4016	1,248	1,070	1,448	13,913	Ferritic			
1.4509	441	4509	1,578	1,352	1,831	17,589	Ferritic			
1.4512	409	4512	1,051	0,902	1,220	11,721	Ferritic			
1.4521	444	4521	2,982	2,558	3,462	33,256	Ferritic			